


URETHANE WARNING TACTILE (BLACK)

P5
GRIP

PRODUCT CODES: DESCRIPTION:

AT 216 SPIKED

RANGE	Warning Tactile
DESIGN	Classic
MATERIAL	UV stabilised thermo plastic urethane (TPU)
LOCATION	Indoor or outdoor
DIMENSIONS	OUTER DIA: 35mm TOP DIA: 25mm THICKNESS: 5mm



CODE AT 216

FIXING Drill and pressure fit
(M8 x 25mm hole)

FEATURES & BENEFITS

Injection moulded, concentric circle design on the horizontal face with a smooth outer edge

Complies with the NCC [D4D9 Tactile Indicators] and Disability (Access to Premises—Buildings) standards to meet the deemed-to-satisfy-provisions

Complies with slip resistance requirements as detailed in HB 198

Identifiable by the unique “double lip” design, providing a distinct advantage when it comes to high slip resistance

Custom colours available (subject to MOQ)

Made in Australia

SLIP RESISTANCE TESTING

Important information: To determine a classification of a slip resistance rating, see Australian Standards Hand Book 198 (HB 198), a Guide to the specification and testing of slip resistance of pedestrian surfaces. This document outlines the minimum ratings of a location and situation of a pedestrian surface.

TEST AS 4586 APPENDIX A: Wet Pendulum Test

FOUR S 96 SLIDER = 73 CLASS = P5

TRL 55 SLIDER = 68 CLASS = P5

TEST AS 4586 APPENDIX C: Wet/Barefoot Ramp Test

MEAN ANGLE OF INCLINATION = 27° CLASS = C

TEST AS 4586 APPENDIX D: Oil/Wet Ramp Test

CORRECTED MEAN OVERALL ACCEPTANCE ANGLE = 23° CLASS = R11

LUMINANCE TESTING

Important information: To determine a luminance contrast between a substrate and the AT TGSI, see: AS/NZS 1428.4.1:2009.

TEST AS/NZS 1428.4.1 APPENDIX E PARAGRAPH E3

LIGHT REFLECTANCE VALUE / WET = 3.37

LIGHT REFLECTANCE VALUE / DRY = 3.50

FIRE TESTING

Important information: The results displayed in this document relate to the behaviour and environment of the product in the conditions to which the test was carried out. This is not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

TEST AS/ISO 9239.1: Reaction to Fire Tests for Floor Coverings

MEAN DISTANCE OF FLAME TRAVEL = 90mm

AVERAGE CRITICAL RADIANT FLUX = $\geq 11\text{kW/m}^2$

AVERAGE INTEGRATED SMOKE VALUE = 47% x min